

Premium 219 Latex

Description

Styrene-butadiene copolymer latex.

Applications

Binder used in running track application for the 1st sprayed tack layer. Product has excellent adhesion to cured asphalt.

Features

- Soft Hand
- Excellent chemical and solvent resistance
- Tough/flexible film properties

Typical Properties

Solids%	44.0 – 47.0
pH	9.0 – 10.0
Viscosity	175cps max
Tg, DSC, °C	-28

Storage and Handling

Protect from freezing. Ideal storage temperature is 22°C (72°F). Stability at 22°C (72°F) is 180 days when properly stored. *Read the DL219 Material Safety Data Sheet before handling, storing, or using this product.*

Packaging Form

Available in 275 gallon Corrugated Liquid Totes or 55 gallon non-returnable drums.

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. We warrant that our products will meet our written specifications. Nothing herein shall constitute and other warranty express or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.



American Recycling Center, Inc

655 Wabasse Drive, Owosso, MI 48867

(989) 725-5100 www.americanrecycling.com