

## Buffings Material

### Description

ARC buffings consist of SBR rubber shaved from the truck tire retreading industry. This product is processed to insure all metal, stone, fiber and all other forms of contaminants from the whole tire is removed. This assures our buffing products will function for a safe resilient surfacing material with superior result.

### Applications

Used in playground cushion layer, Shock pads, and various perform applications. This material can be spreader-applied or paved with the appropriate equipment in conjunction with an approved binder.

ARC buffing rubber is available in two sizes:

- Playground buffing is sized from 4 mesh to 8 mesh
- Track buffing is sized from 8 mesh to 20 mesh.

### Features

- Free of metal, stone, fiber and other contaminants
- Less than 2% dust content
- Sieve analysis standards available upon request

### Physical and Chemical Properties

<u>Test</u>	<u>Result</u>
Specific Gravity	1.15 – 1.25
Hardness (Shore A):	55 – 70
Tensile Strength:	3000 psi
Rubber Hydrocarbon Content:	35% minimum

\*\*Results may vary slightly, relative to the average scrap rubber raw material used.

### Storage and Handling

Keep material dry at all times and out of direct UV contact while in the plastic packaging. *Read the Buffing Material Safety Data Sheet before handling or using this product.*

### Packaging Form

Available in 2000 pound Tote Sacks or palletized in 50 pound clear plastic bags

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. We warrant that our products will meet our written specifications. Nothing herein shall constitute and other warranty express or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.



## American Recycling Center, Inc

655 Wabasse Drive, Owosso, MI 48867

(989) 725-5100 [www.americanrecycling.com](http://www.americanrecycling.com)